

SECTION 404

RECLAIMED PAVEMENT BORROW MATERIAL

DESCRIPTION

404.20 General.

Reclaimed pavement borrow material shall be used for base course and sub-base areas. The material shall be pre-mixed and placed on the sub-grade or sub-base in close conformity with the lines and grades established by the Engineer.

MATERIALS

404.40 General.

Material shall meet the requirements of Subsection M1.11.0 of Division III, Materials.

CONSTRUCTION METHODS

404.60 General.

The reclaimed pavement borrow material shall be spread and compacted in layers not exceeding 200 millimeters in depth, compacted measurement, except the last layer of reclaimed pavement borrow material (conforming to M1.11.0) will be 100 millimeters in depth compacted measurement. The specified density of the Reclaimed Pavement Borrow Material shall be maintained by determining the number of passes of a roller that are required to produce a constant and uniform density, after conducting a series of tests either using the sand/volume method or the nuclear device. The Reclaimed Pavement Borrow Material shall be placed to the tolerance as stipulated in Section 401, Gravel Sub-base.

COMPENSATION

404.80 Method of Measurement.

Reclaimed Pavement Borrow Material shall be measured in place, to the limits specified on the plans or as directed by the Engineer, with no percentage added.

404.81 Basis of Payment.

Reclaimed Pavement Borrow Material will be paid for at the contract unit price per cubic meter complete in place.

404.82 Payment Items.

404.5	Reclaimed Pavement Borrow Material	Cubic Meter
-------	------------------------------------	-------------